



Florida's Paint Manufacturer
Architectural Coatings • Deck Coatings • Roof Coatings • Sundries • Waterproofing Systems

1320 NW 23rd Avenue • Fort Lauderdale, Florida 33311
Broward: 954 581-6060 • Dade: 305 945-4300 • Boca: 561 428-5833
Toll Free: 800 273-1683 • Fax: 954 581-6085

3-2000

ULTRA-PRIME

UNIVERSAL RUST INHIBITIVE FLASH BOND PRIMER INDUSTRIAL COATING

DESCRIPTION: ULTRA-PRIME is a universal solvent based rust inhibitive flash bond primer. ULTRA-PRIME is formulated to solve many painting problems such as adhesion to a variety of metal substrates and other hard to coat surfaces. ULTRA-PRIME protects ferrous metals from rust by incorporating several rust and corrosion resistant pigments that are environmental safe. ULTRA-PRIME may be finish coated with almost any type coating either water based or solvent based. A unique property of ULTRA-PRIME is that it can be top coated with a range of products from two component urethane with high solvency, to acrylic latex, and will still afford the best protection against rust and corrosion..

RECOMMENDED USES: Formulated for use on all types of metal substrates that need rust protection, or that require superior adhesion. Formulated to prime properly prepared steel (ferrous metals), galvanized and aluminum. Excellent for use on either interior and exterior applications.

APPLICATION: Always apply a test sample to previously painted surfaces to check the compatibility of this coating prior to application. ULTRA-PRIME may be applied by roller, brush or spray. Do not apply when temperature is below 50 degrees. Stir and mix thoroughly before use. Thinning is not necessary.

Coverage: 300 to 400 sq. ft. per gallon depending on surface porosity. Always maintain a "wet edge" when brushing or rolling and do not brush or roll back into the painted surface more than five minutes after initial application.

Drytime: Dries to the touch in 45 minutes and can be recoated in 6 hours. Clean tools with xylene immediately after use.

SURFACE PREPARATION

The secret to a successful painting job is the proper surface preparation. All surfaces must be dry and clean from grease, oil, dirt, loose or scaling paint, mildew or algae. Existing RUST should be removed and wire brushed. Severe scaling rust should be sandblasted to white metal for best protection. Allow primer to dry thoroughly prior to painting.

WARNING: All factory primed and previously painted surfaces should be tested for adhesion prior to application of this or any coating.

CAUTION: Do not take internally. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close the container after use. Do not apply at temperatures below 50° F.

TECHNICAL	Pigment by weight	44.50%	Total solids by volume	49.5%
	Vehicle by weight	55.50%	Total solids by weight	65.80%
	Weight by gallon	11.35 lbs.	Finish	FLAT

KEEP OUT OF REACH OF CHILDREN